


















	PROPRIETÀ / PROPERTY	STANDARD	TILE	 HDF Click-system autoposante / loose - lay
	Surface treatment Trattamento superficiale		HotCoating	HotCoating
	Environmental sustainability Sostenibilità ambientale		100%	100%
	Dimensions & thickness Dimensioni e spessore	EN 427 & EN 428	600 x 600 x 5 mm 600 x 1200 x 5 mm 620 x 450 x 5 mm 915 x 305 x 5 mm 1235 x 200 x 5 mm 1235 x 305 x 5 mm 1815 x 200 x 5 mm	620 x 450 x 10 mm 915 x 305 x 10 mm 1235 x 200 x 10 mm 1235 x 305 x 10 mm 1815 x 200 x 10 mm
	European classification Classificazione europea	EN 16511	domestic 23 commercial 33	domestic 23 commercial 33
	Total weight Peso totale	EN 430	ca. 3.000 g/m <sup>2</sup>	ca. 8.600 g/m <sup>2</sup>
	Abrasion resistance Resistenza all'abrasione	EN 14354 & EN 13329	AC5	AC5
	Impact sound reduction Riduzione suono da impatto	EN ISO 717-2	17 dB	17 dB
	Castro chair test Test sedia a rotelle	EN 425	suitable for type W	suitable for type W
	Fire reaction Reazione al fuoco	EN 13501-1	Cfl s1	Cfl s1
	Thermal resistance Resistenza termica	EN 12524	0,058 m <sup>2</sup> K/W	0,080 m <sup>2</sup> K/W
	Dimensional stability Stabilità dimensionale	EN 434	< 0,10 %	< 0,05 %
	Residual indentation Impronta residua	EN 433	max. 0,25 mm	max. 0,15 mm
	Resistance to chemicals Resistenza ai prodotti chimici	EN 423	very good resistance	very good resistance
	Absorption capacity (24h) Capacità di assorbimento (24h)	EN 317	0 %	< 8 %
	Weight resistance Resistenza al carico	EN 51130	2.000 / 14 mm	2.000 / 14 mm
	Slip resistance Resistenza allo scivolamento	BCRA	μ ≥ 0,40	μ ≥ 0,40
		DIN 51130	R 10	R 10